



Gmund Manteco

PRINTING INFORMATION

Printing	- Offset printing (colored papers: limited suitability) - Letterpress - Silkscreen - Blind embossing - Hot-foil stamping - Stamping
Recommendations for offset printing	- Screens up to 80 l/cm - Match lith to the paper colour - Proof printing on same paper sock - Under color reduction (UCR) when applying strong ink coverage - Deposits inclusions on the offset blanket are avoidable and require regular cleansing of the rubber blankets. Tiny cotton particles can separate from the surface here. Low absorption of the printing ink, therefore: - Use of fully oxidative inks - For uncoated paper use soft rubber blankets (low shore-hardness) - Print dusting, low printing stack - Dry thoroughly for a minimum of 24 hours
Special advice	- Not suitable for laser and inkjet printers - Inclusions, the look of the sheet and the color may vary slightly from one fabrication to the next due to the composition of the materials and the utilization of cotton fibres from the textile industry. - Natural papers have a top side and a bottom side. It is recommended, to use the top side as front side for the print project. - The special character of Gmund Manteco looks best when little ink is used, with blind embossing and in letterpress printing. - The printing technique should be adapted to suit the unusual surface of the paper. - When printing and processing, follow the manufacturer's recommendations for machines, printing inks, adhesives, laminating foils, stamping foils, etc. Gmund accepts no liability for damage resulting from incorrect use.
Further information	- www.gmund.com